

Technical Note

Evaluation of mechanical rock properties using a Schmidt Hammer

O. Katz^{1,2,3}, Z. Reches¹, J-C. Roegiers³

1. Institute of Earth Sciences, Hebrew University, Givat-Ram Campus, Jerusalem 91904, Israel

2. Geological Survey of Israel, 30 Malkhe Yisrael st., Jerusalem 95501, Israel

3. Rock Mechanics Inst., University of OK, 100 E. Boyd st. Norman, OK 73019, USA

Introduction

The Schmidt Hammer was developed in 1948 for non-destructive testing of concrete hardness [1], and later to estimate rock strength [2,3]. It consists of a spring-loaded mass that is released against a plunger when the hammer is pressed onto a hard surface. The plunger impacts the surface and the mass recoils; the rebound value of the mass is measured either by a sliding pointer or electronically. Hammer rebound readings are considered consistent and reproducible [4,5,6]. Such fast, non-destructive and in-situ evaluations of rock mechanical parameters reduce the expenses for sample collection and laboratory testing. Consequently, the mechanical parameters can be determined in dense arrays of field measurements that reflect the real inherent inhomogeneity of rock masses [7].

Schmidt Hammers were used to estimate strength of concrete and rocks [2,8,9,10,11] via empirical correlations between rebound readings and compressive strength determined from standard tests [2,8,11]. This technical note extends these correlations, and we present new and reliable correlations between rebound readings of seven rock types and their measured laboratory values of Young's modulus, uniaxial compressive strength and density. The studied rocks include soft chalk, limestones, sandstone and stiff igneous rocks, covering the entire practical range of rock elasticity. These new correlations were already used for a detailed field study of rock damage [7].

Analysis

Materials and Methods

Seven rocks were analyzed: Maresha chalk, Cordoba-Cream limestone, Berea sandstone, Indiana limestone, Carrara marble, Gevanim syenite and Mt. Scott granite. The sources and features of these rocks are listed in Table 1.

A digital concrete hammer, model 58-C181/F, made by Controls with impact energy of 2.207 Joules was used. This model complies with the following standards: ASTM C 805, UNI 9189-88, BS 1881, NF P18-417, DIN 1048, ISO/DIN 8045. A well-calibrated hammer of these standards is expected to generate the same readings as presented here.

Hammer readings were determined on samples of the following sizes: NX size (54 mm diameter) cores for Maresha chalk, Cordoba Cream limestone, Berea sandstone, Gevanim syenite and Mt. Scott granite; a 40mm thick slab of Carrara marble and a 100mm thick block of Indiana limestone. Each sample was inspected for macroscopic defects to avoid testing near fractures or material inhomogeneities. In both geometries the tested faces were smooth and the hammer tests were performed according to the Recommended Procedure of the International Society for Rock Mechanics [9]. Core samples were placed in a 40 kg

steel V-block while the rectangular samples were clamped to the flat side of the V-block. Tens individual impacts were conducted on each sample with a minimal separation of the plunger diameter between impacts location. This separation ensures that the impacts hit undamaged rock. Tests that caused cracking or other visible damage were rejected. The rebound value reported here is the average of the upper 50% of 32-40 individual impacts; averages and standard deviations are listed in Table 2. Samples of Maresha chalk yielded after few hammer impacts, and thus only the first seven readings are used here.

The mechanical properties of the studied rocks (Young's modulus and strength) were compiled from several sources listed in Table 2. The uniaxial compressive strength and Young's modulus of Gevanim syenite and Mt. Scott granite were measured at the Rock Mechanics Institute, University of Oklahoma. The densities of Maresha chalk, Cordoba Cream limestone, Berea sandstone, Indiana limestone, Gevanim syenite and Mt. Scott granite were calculated from oven-dry weight of core samples. The density of the Carrara marble is after Carmichael [12].

Rock name	Type /texture	Composition (main/minor)	Grain size	Porosity	Origin [Ref.]
Maresha chalk	Sedimentary/ fine granular, slightly cemented	Calcite/ clay	Fine	52-60%	Bet Guvrin, Israel [13]
Cordoba Cream limestone	Sedimentary/ fine granular, slightly cemented	Calcite (85%), clay (14%), quartz (1%)	Fine	23%	Austin, Texas [14]
Berea sandstone	Sedimentary/ granular, cemented	quartz (80%) feldspar (5%), calcite (6%) clay (8%)	0.25 mm	19%	Amherst, Ohio[15]
Indiana limestone	Sedimentary/ Granular, cemented	Calcite (98%), minor dolomite	Fine	18%	Bedford, Indiana [15]
Carrara marble	Metamorphic/ crystalline	Calcite (99%), minor quartz	0.15 mm	Low	Carrara, Italy [16]
Gevanim syenite	Igneous/ crystalline	Feldspar, quartz, and minor mafic	0.25-1 mm	Low	Ramon, Israel [This work]
Mt. Scott granite	Igneous/ crystalline	Feldspar, quartz, and minor mafic	1-3 mm	Low	Wichita Mts. Oklahoma [17]

Table 1. Mineralogical and lithological properties of the investigated rocks.

Rock name	Schmidt Hammer data (this work)		Young's modulus-E (GPa)	Density-D (kg m ⁻³)	Uniaxial strength-C ₀ (MPa)	Source of E
	Mean rebound	Standard deviation				
Maresha chalk	23.9	1.4	2.4 ± 1.1	1,220	11	[13]
Cordoba-C limestone	41.5	2.2	12.5 ± 0.96	2,070	32	[14]
Berea sandstone	50.8	1.9	19.3	2,100	74	[12]
Indiana limestone	50.6	1.2	25.3 ± 1.2	2,360	62	[18]
Carrara marble	58.6	0.8	39.2 ± 5.6	2,710	95	[16]
Gevanim syenite	65.0	1.9	53.4 ± 2.4	2,468	259	This work
Mt. Scott granite	73.4	2.7	75.6	2,650	243	This work

Table 2. List of Schmidt Hammer data and mechanical properties of the investigated rocks.

Results: Empirical correlation parameters

The measured mechanical values display a wide range of properties (Table 2). The hammer-rebound range of 23.9-73.4 corresponds to Young's moduli ranging from 2 to 76 GPa, uniaxial strength varying from 11 to 259 MPa, and density range of 1200-2650 kg m⁻³. The measured values shown in Figures 1-3 were used to determine the best empirical correlations between hammer rebound and the mechanical properties. The three properties have three different functional relations to HR as shown in equations (1)-(3) below. These equations present the correlation parameters and correlation factor R for Young's modulus E (in GPa), uniaxial compressive strength U (in MPa), and density D (in kg m⁻³). The third term on the right side of each equation is the standard error for the estimation of the relevant variable.

$$\ln(E) \text{ (in GPa)} = -8.967 + 3.091 * \ln(HR) \pm 0.101 \text{ (R}^2 = 0.994) \text{ (1)}$$

$$\ln(U) \text{ (in MPa)} = 0.792 + 0.067 * (HR) \pm 0.231 \text{ (R}^2 = 0.964) \text{ (2)}$$

$$D \text{ (in kg m}^{-3}\text{)} = -2874 + 1308 * \ln(HR) \pm 164.0 \text{ (R}^2 = 0.913) \text{ (3)}$$

Figure 1. Empirical relations between hammer rebound values and the measured Young's modulus. Heavy line is the best-fit correlation (eq. 1 in text); horizontal error bars indicate standard deviations of the hammer rebound measurements. Hammer measurements conducted in the present study (see text); Young's modulus sources are listed in Table 2.

Figure 2. Empirical relations between hammer rebound values and the measured uniaxial compressive strength. Heavy line is the best-fit correlation (eq. 2 in text); horizontal error bars indicate standard deviations of the hammer rebound measurements. Hammer measurements conducted in the present study (see text); sources of strength values are listed in Table 2. For legend see Figure 1.

Figure 3. Empirical relations between hammer rebound values and the measured dry density. Heavy line is the best-fit correlation (eq. 2 in text); horizontal error bars indicate standard deviations of the hammer rebound measurements. Hammer and density measurements conducted in the present study (see text); density of Carrara marble after [12]. For legend see F11.

Applications

Usage of hammer rebound values

Hammer reading values reflect an interrelated combination of rock properties such as elastic modulus, strength, hardness, surface smoothness, density and cementation. In the present work, we found good correlations between HR values and three specific rock properties: Young modulus, uniaxial compressive strength and density (eqs. 1-3). However, HR values may also display good correlation with a combination of several mechanical properties, for example, correlation of HR with the product of log strength and density [2]. Further, HR could be correlated with practical parameters such as tunnel boring performance (Hudson J. A., written communication), or with RQD values. We found that a quantitative evaluation of a specific property with hammer readings requires some precaution as discussed below.

Conditions in field work

We used the Schmidt Hammer for a field survey in an intrusive rock body composed of fine-grained quartz-syenite (granite like), in Ramon, southern Israel [7]. At this site the rock properties and rock structure within a faulted region were mapped in detail. The field measurements were performed on three types of surfaces: naturally weathered rock surfaces, rock surfaces polished manually with the grinding stone provided by the hammer manufacturer and surfaces polished with an electrical grinder. The grinding effectively cleans the inspected surface from the outermost weathered layer and exposes the intact rock. The values and repeatability of the hammer readings increase with intensity of polishing. For six test sites surveyed according to ISRM [9], the standard deviation was 5.57 ± 1.69 for naturally weathered surfaces, 3.80 ± 1.41 for surfaces polished manually, and $1.93 \pm$

1.34 for surfaces polished with an electrical grinder. Clearly, the high-quality polishing profoundly improved the quality of field measurements.

Another precaution in the field is the proximity to fractures that may reduce HR readings due to displacement or shaking. The measurement of a loose or fractured block provides reliable HR value if the block weighs a few tens of kilograms or more.

Rock type

We think that the good correlations observed here, and particularly the excellent fit of Young modulus [Fig. 1 and eq. 1], indicate that the used rocks are well cemented and elastic. Poorly cemented, friable rocks, that disintegrate or fracture under the hammer impact, could provide less consistent correlation. This dependence on rock type was demonstrated by Cargill and Shakoor [2]. They analyzed hammer rebound data for 13 rock types, and correlated the logarithm of the uniaxial compressive strength with the product of dry density, D , and hammer rebound, HR , i.e.

$$\log(U) = k (D HR)$$

where k is a constant. These authors derived two different curves, one for sandstones and one for carbonates, and suggested that the results are sensitive to the rock type.

Conclusions

Empirical correlations between rebound reading of Schmidt Hammer and laboratory measured values of Young's modulus, uniaxial strength and dry density were presented (Figs. 1-3). The correlation factors of equations 1-3 can be used to estimate the relevant mechanical properties in the field and laboratory under the following precautions:

- a. The tested rock is well-cemented and apparently elastic;
- b. Rocks that tend to disintegrate under hammer impact or samples that crack under the impacts cannot be properly estimated;
- c. Hammer measurements should be conducted on smooth surfaces; polishing with an electric grinder is strongly recommended for fieldwork; and
- d. Loose blocks (or fractured blocks) can be measured if the intact part of the block weighs a few tens of kilograms or more.

Acknowledgements

The laboratory work was conducted at the Rock Mechanics Institute, University of Oklahoma, Norman, with the invaluable help and advise of Gene Scott and Pete Keller. Many thanks to Sankar Muhuri, Charles Gilbert, Thomas Dewers and Yossef Hatzor who kindly provided samples for this study. The study was supported by an Internal Fund of the Hebrew University for "Fault nucleation", by the Geological Survey of Israel project 30255, by Eberly Family Chair funds from M. Charles Gilbert, and by the Rock Mechanics Institute, Uni. of OK, Norman.

References

1. Schmidt E., A non-destructive concrete tester. *Concrete*, 1951, **59**, 8, 34-35.
2. Cargill J. S. and Shakoor A., Evaluation of empirical methods for measuring the uniaxial compressive strength of rock. *Int. J. Rock Mech. Min. Sci. & Geomech. Abst.*, 1990, **27**, 495-503.
3. Israely A. A., Study of the engineering-geological characteristics of the bedrock in the Jerusalem area; Geological map, scale 1:100000 (in Hebrew), *M.Sc. thesis*, The Hebrew University Jerusalem., 1973.

4. Poole R. W. and Farmer I. W., Consistency and repeatability of Schmidt Hammer rebound data during field testing. *Int. J. Rock Mech. Min. Sci. & Geomech. Abst.*, 1980, **17**, 167-171.
5. Goktan R. M. and Ayday C. A., Suggested improvement to the Schmidt rebound hardness ISRM suggested methods with particular reference to rock machineability. *Int. J. Rock Mech. Min. Sci. & Geomech. Abst.*, 1993, **30**, 321-322.
6. Day M. J. and Goudie A. S., Field assessment of rock hardness using the Schmidt Test Hammer. *British Geomorph. Res. Gp. Tech. Bull.*, 1997, **18**, 19-29.
7. Katz, O., Reches, Z., Lyakhovsky, V. and Baer G., Rock Damage at the Proximity of Small Faults: Field Measurements of Elastic Wave Velocity and Elastic Rebound. In AGU 1999 Spring Meeting, *EOS, Transaction, American Geophysical Union*, 1999, **80**, 17 Supplement, 335-336.
8. Hucka V. A rapid method of determining the strength of rocks in situ. *Int. J. Rock Mech. Min. Sci. & Geomech. Abst.*, 1965, **2**, 127-134.
9. ISRM. Suggested methods for determining hardness and abrasiveness of rocks. *Int. J. Rock Mech. Min. Sci. & Geomech. Abst.*, 1987, **15**, 89-97.
10. Kolaiti E. and Papadopoulos Z. Evaluation of Schmidt rebound hammer testing: a critical approach. *Bulletin of the Inter. Ass. of Engineering Geology.*, 1993, **48**, 69-76.
11. Yaalon D. H. and Singer S., Vertical variation in strength and porosity of calcrete (nari) on chalk, Shefela, Israel and interpretation of its origin. *Journal of sedimentary Petrology*, 1974, **44**, 4, 1016-1023.
12. Carmichael, R.C., *CRC practical handbook of physical properties of rock and minerals*. CRC Press Inc, 1989, pp. 226-227.
13. Tsesarsky M., Stability of underground openings in jointed chalk rock - A case study from bell shaped caverns, Bet Guvrin National Park. *M.Sc. Thesis*, Ben Gurion University of the Negev, Beer - Sheva, Israel 1999.
14. Azeemuddin M., Pore collapse in weak rocks, *Ph.D. dissertation*, University of Oklahoma, Norman OK, 1995.
15. Hart D. J. and Wang H. F., Laboratory measurements of a complete set of poroelastic moduli for Berea Sandstone and Indiana Limestone. *J. Geophys. Res.*, **100**, 9, 1995, 17741-17751.
16. Fredrich J. T. Evans B. and Wong T. F., Micromechanics of the brittle to plastic transition in Carrara Marble. *J. Geophys. Res.*, **94**, 4, 1989, 4129-4145.
17. Price, J. D., Hogan, J. P., Gilbert, M. C., and Payne, J. D., Surface and near-surface investigation of the alteration of the Mount Scott Granite and geometry of the Sandy Creek Gabbro pluton, Hale Spring area, Wichita Mountains, Oklahoma. In *Basement Tectonics*, Vol. 12. Kluwer Academic Publishers, 1998, pp.79-122.
18. Wawersik W. R. and Fairhurst C., A study of brittle fractures in laboratory compressive experiments. *Int. J. Rock Mech. Min. Sci. & Geomech. Abst.*, 1970, **7**, 561-575.